

RUBBER SEALANT

Description

Quick-setting neutral elastomeric sealant with outstanding resistance to ageing, UV radiation, light, moisture and temperature under all weather conditions. Used for sealing between waterproofing membranes and end strips, vents, drains, etc.).

Features		
Shore A Hardness	ISO 868	25
Tensile strength	ISO 8339	0.6 N/mm ²
Ultimate elongation	ISO 8339	400%
Service temperature limits		-50/+150°C

Packaging

- 310 ml PE polyethylene cartridge.
- Carton with 12 cartridges.
- Weight: 6 kg/carton.
- ADR land transport classification: not classified.

Standard colours

Grey.

Yield

 5×5 mm bead 13 m/cartridge 10 \times 5 mm bead 6.5 m/cartridge

Application

- Substrate must be clean, dry and uncontaminated.
- Smooth sealant bead using a squeegee dipped in soapy water.
- Application temperature from +5°C to +40°C(*).
- See RUBBERFUSE Division specifications and instructions.

Note: (*) Preheating is recommended if product is applied at temperatures below 10°C.

Safety regulations

- Avoid contact with skin.
- In case of contact with eyes, rinse immediately with plenty of water.
- When using do not eat, drink or smoke.
- Wash hands with soap and water after use.
- Refer to the EC Safety Data Sheet.



Rev. 00 (11-15)

As IMPER ITALIA srl has no control over how or where its products are supplied (e.g., over substrates, service conditions, or compliance with instructions), the company cannot accept any liability arising from the use of its product or the results obtained. IMPER ITALIA srl pursues a policy of continuous product improvement. As a result, the company reserves the right to make any necessary changes to the information contained in this publication at any time and without notice.



 Imper Italia srl
 Via Volta, 8 · 10071

 Frazione Mappano · Borgaro (TO) Italy

 Tel (+39) 011 222.54.99 · Fax (+39) 011 222.54.80

 export@imper.it · www.imper.it

RUBBERFUSE DIVISION Via Volta, 9 · 10071 Fraz. Mappano · Borgaro (TO) Italy · Tel (+39) 011 222.54.99 · Fax (+39) 011 262.51.87 · rubberfuse@imper.it